

Magnetische Eigenschaften gebundener NdFeB-Magnete

		Remanenz		Koerzitivfeldstärke				Energieprodukt		Temp. Coeff. Hcj	Dichte
Typ		Br		Hcb		Hcj		(BH)max.		(%/°C)	(g/cm³)
		kG	T	kOe	kA/m	kOe	kA/m	MGOe	kJ/m³		

NBC8	max	6.5	0.65	5.7	454	17.0	1353	9.0	72	-0.15	6.1
	min	5.8	0.58	4.9	390	13.0	1035	7.5	60		5.6
NBC9L	max	7.1	0.71	5.9	470	10.0	796	10.0	80	-0.10	6.1
	min	6.4	0.64	5.1	406	8.0	637	8.5	68		5.6
NBC10	max	6.5	0.65	5.7	454	17.0	1353	11.0	88	-0.15	6.1
	min	5.8	0.58	4.9	390	13.0	1035	9.0	72		5.6
NBC11	max	6.5	0.65	5.7	454	14.0	1114	12.0	96	-0.12	6.1
	min	5.8	0.58	4.9	390	11.0	876	10.0	80		5.6

NB14L	max	4.9	0.49	3.9	310	9.2	732	4.5	36	-0.10	4.9
	min	4.1	0.41	3.1	247	7.2	573	3.5	28		4.2
NB16	max	5.6	0.56	5.0	398	17.0	1353	6.5	52	-0.15	5.5
	min	4.8	0.48	4.2	334	13.0	1035	5.0	40		5.0
NB16L	max	6.2	0.62	5.1	406	10.0	796	7.7	61	-0.10	5.5
	min	5.4	0.54	4.3	342	8.0	637	6.2	49		5.0
NB18L	max	6.3	0.63	5.4	430	10.5	835	8.4	67	-0.10	5.5
	min	5.7	0.57	4.8	382	8.5	676	7.4	59		5.0